IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Previously Presented): A phosphor comprising a crystal phase having any one chemical composition of the following formulas [1] to [3]:

$$Eu_{s0}Mn_{b0}M^{10}_{c0}M^{20}_{d0}M^{30}O_{c0}Z^{0}_{m}$$
 [1]

wherein M^{10} is a divalent element containing 85 mol% or more of at least one element selected from the group consisting of Ba, Ca and Sr, in which the ratio (molar ratio) of Ca to the sum of Ba and Ca is from 0.1 to 0.9; M^{20} represents at least one element selected from the group consisting of a monovalent, trivalent and pentavalent elements; M^{30} represents a group of tetravalent elements containing Si and Ge in a total amount of 90 mol% or more; Z^0 is at least one element selected from the group consisting of a minus monovalent and minus divalent elements, H and N; and a0 is a number satisfying $0.001 \le 0.06$, b0 is a number satisfying $0.001 \le 0.06$, c0 and d0 are numbers satisfying $0.001 \le 0.06$, a0, b0 c0 and d0 are numbers satisfying $1.8 \le (0.0+0.0+0.0) \le 0.2$, and e0 and f0 are numbers satisfying $0.001 \le 0.001$ and $0.001 \le 0.$

$$Eu_{a1}Mn_{b1}Mg_{c1}M^{11}_{d1}M^{21}O_{c1}Z^{1}_{f1}$$
 [2]

wherein M^{11} represents at least one element selected from the group consisting of a monovalent element, a divalent element except Eu, Mn and Mg, a trivalent element and a pentavalent element, in which the proportion of the divalent element is 80 mol% or more, the proportion of the sum of Ba, Ca and Sr is 40mol% or more, and the ratio (molar ratio) of Ca to the sum of Ba and Ca is from 0.2 to 0.9; M^{21} represents a group of tetravalent elements containing Si and Ge in a total amount of 90 mol% or more; Z^1 is at least one element selected from the group consisting of a minus monovalent and minus divalent elements, H and N; and a1 is a number satisfying $0.001 \le a1 \le 0.8$, b1 is a number satisfying $0 < b1 \le 0.8$, c1 and d1 are numbers satisfying $0 < c1/(c1+d1) \le 0.2$, a1, b1 c1 and d1 are numbers satisfying

 $1.8 \le (a1+b1+c1+d1) \le 2.2$, and e1 and f1 are numbers satisfying $0 \le f1/(e1+f1) \le 0.035$ and $3.6 \le (e1+f1) \le 4.4$:

$$Eu_{a2}Mn_{b2}Mg_{c2}M^{12}_{d2}M^{22}O_{e2}Z^{2}_{f2}$$
 [3]

wherein M^{12} represents at least one element selected from the group consisting of a monovalent element, a divalent element except Eu, Mn and Mg, a trivalent element and a pentavalent element, in which the proportion of the divalent element is 80 mol% or more, the proportion of the sum of Ba, Ca and Sr is 40mol% or more, and the ratio (molar ratio) of Ca to the sum of Ba and Ca is less than 0.2; M^{22} represents a group of tetravalent elements containing Si and Ge in a total amount of 90 mol% or more; Z^2 is at least one element selected from the group consisting of a minus monovalent and minus divalent elements, H and N; and a2 is a number satisfying $0.0003 \le a2 \le 0.8$, b2 is a number satisfying $0.002 \le 0.8$, c2 and d2 are numbers satisfying $0.002 \le 0.8$, a2, b2 c2 and d2 are numbers satisfying $0.002 \le 0.8$, a2, b2 c2 and d2 are numbers satisfying $0.002 \le 0.8$, a2, b2 c3 and d2 are numbers satisfying $0.002 \le 0.8$, a2, b3 and a2 are numbers satisfying $0.002 \le 0.8$, a2, b3 and a3 and a5 and a6 are numbers satisfying $0.002 \le 0.8$, a2, b3 and a3 and a5 and

Claim 2 (Previously Presented): The phosphor according to claim 1 comprising a crystal phase having a chemical composition of said formula [1], wherein M^{10} is a divalent element containing 85 mol% or more of at least one element selected from the group consisting of Ba, Ca and Sr, in which the ratio (molar ratio) of Ca to the sum of Ba and Ca is from 0.2 to 0.8; M^{20} represents at least one element selected from the group consisting of a monovalent, trivalent and pentavalent elements; M^{30} is Si; Z^0 is at least one element selected from the group consisting of a minus monovalent and minus divalent elements, H and N; and a0 is a number satisfying $0.02 < a0 \le 0.5$, b0 is a number satisfying $0 < b0 \le 0.7$, c0 and d0 are numbers satisfying $0.02 < a0 \le 0.1$, a0, b0 c0 and d0 are numbers satisfying

 $1.9 \le (a0+b0+c0+d0) \le 2.1$, and e0 and f0 are numbers satisfying $0 \le f0/(e0+f0) \le 0.01$ and $3.8 \le (e0+f0) \le 4.2$.

Claim 3 (Previously Presented): The phosphor according to claim 1 comprising a crystal phase having a chemical composition of said formula [2], wherein M^{11} represents at least one element selected from the group consisting of a monovalent element, a divalent element except Eu, Mn and Mg, a trivalent element and a pentavalent element, in which at least one element selected from the group consisting of Ba, Ca and Sr is contained in an amount of 85mol% or more, and the ratio (molar ratio) of Ca to the sum of Ba and Ca is from 0.2 to 0.8; M^{21} is Si; Z^1 is at least one element selected from the group consisting of a minus monovalent and minus divalent elements, H and N; and a1 is a number satisfying $0.01 < a1 \le 0.5$, b1 is a number satisfying $0.01 < a1 \le 0.5$, b1 is a number satisfying $0.01 < a1 \le 0.5$, a1, b1 c1 and d1 are numbers satisfying $1.9 \le (a1+b1+c1+d1) \le 2.1$, and e1 and f1 are numbers satisfying $0.01 < a1 \le 0.5$.

Claim 4 (Previously Presented): The phosphor according to claim 1 comprising a crystal phase having a chemical composition of said formula [3], wherein M^{12} represents at least one element selected from the group consisting of a monovalent element, a divalent element except Eu, Mn and Mg, a trivalent element and a pentavalent element, in which the proportion of the divalent element is 80 mol% or more, the proportion of the sum of Ba, Ca and Sr is 40mol% or more, and the ratio (molar ratio) of Ca to the sum of Ba and Ca is less than 0.2; M^{22} represents a group of tetravalent elements containing Si and Ge in a total amount of 90 mol% or more; Z^2 is at least one element selected from the group consisting of a minus monovalent and minus divalent elements, H and N; and a2 is a number satisfying $0.01 \le a2 \le 0.5$, b2 is a number satisfying $0.01 \le a2 \le 0.5$, b2 is a number satisfying

Docket No. 293774US Preliminary Amendment

 $0 < c2/(c2+d2) \le 0.2$ or $0.3 \le c2/(c2+d2) \le 0.7$, a2, b2 c2 and d2 are numbers satisfying $1.9 \le (a2+b2+c2+d2) \le 2.1$, and e2 and f2 are numbers satisfying $0 \le f2/(e2+f2) \le 0.01$ and $3.8 \le (e2+f2) \le 4.2$.

Claim 5 (Previously Presented): The phosphor according to claim 1, wherein the phosphor comprises a specified crystal phase obtained from X-ray diffraction measurement, wherein the crystal phase satisfies the following conditions:

(Conditions)

In X-ray diffraction measurement using a CuK α as an X-ray source, a diffraction peak is observed within the range (R0) of the diffraction angle (2 θ) of from 21.30° to 22.50°, and when this diffraction peak is taken as a reference diffraction peak (P0) and 5 diffraction angle ranges derived from the Bragg angle (θ s) of P0 are taken as R1, R2, R3, R4 and R5, at least one diffraction peak exists in these 5 ranges, with the proviso that P0 has an intensity of 20% or more by the diffraction peak height ratio, based on the strongest diffraction peak of said 6 or more crystal phase-derived diffraction peaks, and the other peaks has an intensity of 9% or more by the diffraction peak height ratio, wherein when two or more diffraction peaks exist in one angle range, a peak higher in intensity is selected.

R1: $2 \times \arcsin\{\sin(\theta 0)/(0.720 \times 1.015)\}\$ to $2 \times \arcsin\{\sin(\theta 0)/(0.720 \times 0.985)\}\$

R2: $2 \times \arcsin\{\sin(\theta 0)/(0.698 \times 1.015)\}\$ to $2 \times \arcsin\{\sin(\theta 0)/(0.698 \times 0.985)\}\$

R3: $2 \times \arcsin \{ \sin(\theta 0) / (0.592 \times 1.015) \}$ to $2 \times \arcsin \{ \sin(\theta 0) / (0.592 \times 0.985) \}$

R4: $2 \times \arcsin\{\sin(\theta 0)/(0.572 \times 1.015)\}\$ to $2 \times \arcsin\{\sin(\theta 0)/(0.572 \times 0.985)\}\$

R5: $2 \times \arcsin\{\sin(\theta 0)/(0.500 \times 1.015)\}\$ to $2 \times \arcsin\{\sin(\theta 0)/(0.500 \times 0.985)\}\$

Claim 6 (Previously Presented): The phosphor according to claim 1, wherein said crystal phase satisfies the following conditions:

(Conditions)

In X-ray diffraction measurement using a $CuK\alpha$ as an X-ray source, a diffraction peak is observed within the range (R0) of the diffraction angle (20) from 21.30° to 22.50°, and when this diffraction peak is taken as a reference diffraction peak (P0) and 5 diffraction angle ranges derived from the Bragg angle (0s) of P0 are taken as R1, R2, R3, R4 and R5, at least one diffraction peak exists in these 5 ranges, with the proviso that P0 has an intensity of 20% or more by the diffraction peak height ratio, based on the strongest diffraction peak of 6 or more crystal phase-derived diffraction peaks, and the other peaks has an intensity of 9% or more by the diffraction peak height ratio, wherein when two or more diffraction peaks exist in one angle range, a peak higher in intensity is selected.

R1: $2 \times \arcsin\{\sin(\theta 0)/(0.720 \times 1.010)\}\$ to $2 \times \arcsin\{\sin(\theta 0)/(0.720 \times 0.990)\}\$

R2: $2 \times \arcsin \{ \sin(\theta 0) / (0.698 \times 1.010) \}$ to $2 \times \arcsin \{ \sin(\theta 0) / (0.698 \times 0.990) \}$

R3: $2 \times \arcsin\{\sin(\theta 0)/(0.592 \times 1.010)\}\$ to $2 \times \arcsin\{\sin(\theta 0)/(0.592 \times 0.990)\}\$

R4: $2 \times \arcsin\{\sin(\theta 0)/(0.572 \times 1.010)\}\$ to $2 \times \arcsin\{\sin(\theta 0)/(0.572 \times 0.990)\}\$

R5: $2 \times \arcsin\{\sin(\theta 0)/(0.500 \times 1.010)\}\$ to $2 \times \arcsin\{\sin(\theta 0)/(0.500 \times 0.990)\}\$

Claim 7 (Original): A phosphor comprising a crystal phase of an alkali earth silicate containing at least one element selected from the group consisting of Ba, Sr, Ca and Mg, wherein said crystal phase is a crystal phase satisfying the following conditions:

(Conditions)

In X-ray diffraction measurement using a CuK α as an X-ray source, a diffraction peak is observed within the range (R0) of the diffraction angle (2 θ) from 21.30° to 22.50°, and when this diffraction peak is taken as a reference diffraction peak (P0) and 5 diffraction angle ranges derived from the Bragg angle (θ s) of P0 are taken as R1, R2, R3, R4 and R5, at least one diffraction peak exists in these 5 ranges, with the proviso that P0 has an intensity of 20%

or more by the diffraction peak height ratio, based on the strongest diffraction peak of said 6 or more crystal phase-derived diffraction peaks, and the other peaks has an intensity of 9% or more by the diffraction peak height ratio, wherein when two or more diffraction peaks exist in one angle range. a peak higher in intensity is selected.

R1: $2 \times \arcsin\{\sin(\theta 0)/(0.720 \times 1.010)\}\$ to $2 \times \arcsin\{\sin(\theta 0)/(0.720 \times 0.990)\}\$

R2: $2 \times \arcsin \{ \sin(\theta 0) / (0.698 \times 1.010) \}$ to $2 \times \arcsin \{ \sin(\theta 0) / (0.698 \times 0.990) \}$

R3: $2 \times \arcsin\{\sin(\theta 0)/(0.592 \times 1.010)\}\$ to $2 \times \arcsin\{\sin(\theta 0)/(0.592 \times 0.990)\}\$

R4: $2 \times \arcsin \{ \sin(\theta 0) / (0.572 \times 1.010) \}$ to $2 \times \arcsin \{ \sin(\theta 0) / (0.572 \times 0.990) \}$

R5: $2 \times \arcsin \{ \sin(\theta 0) / (0.500 \times 1.010) \}$ to $2 \times \arcsin \{ \sin(\theta 0) / (0.500 \times 0.990) \}$

Claim 8 (Previously Presented): A light emitting device comprising a first light emitter which emits light of 350 nm to 430 nm and a second light emitter which emits visible light by irradiation of light from the first light emitter, wherein the second light emitter contains the phosphor according to claim 1.

Claim 9 (Original): The light emitting device according to claim 8, wherein the first light emitter is a laser diode or a light emitting diode.

Claim 10 (Previously Presented): A lighting system comprising the light emitting device according to claim 8.

Claim 11 (Previously Presented): An image display unit comprising the light emitting device according to claim 8.

Claim 12 (New): The phosphor according to claim 1, which emits white light.

Docket No. 293774US Preliminary Amendment

Claim 13 (New): The phosphor according to claim 1, which emits red light.

Claim 14 (New): A method of producing the phosphor according to Claim 1, which comprises preparing a mixture of sources and burning the mixture by heat treatment under a heating atmosphere, wherein the heating atmosphere is a reducing atmosphere.

Claim 15 (New): A phosphor-containing resin wherein the phosphor according to Claim 1 is dispersed in a resin.

Claim 16 (New): The light emitting device according to Claim 8, which uses a GaN-based compound semiconductor as the first light emitter.

Claim 17 (New): The light emitting device according to Claim 8, which emits white light.

Claim 18 (New): The light emitting device according to Claim 8, which emits red light.